

AMENDMENTS TO THE CLAIMS

1. (Original) A film-type catalyst for production of a tertiary amine, which is used in producing a tertiary amine from an alcohol and a primary or secondary amine as the starting material.
2. (Original) The film-type catalyst according to claim 1, which has a thickness of 100 μm or less.
3. (Original) The film-type catalyst according to claim 1 or 2, which comprises copper.
4. (Currently amended) The film-type catalyst according to ~~any of claims 1 to 3~~ claim 1 or 2, which is fixed on the surface of a substrate.
5. (Currently amended) The film-type catalyst according to ~~any of claims 1 to 4~~ claim 1, which has a pore volume of 0.5 to 30 mL/m² and comprises synthetic resin in an amount of 20 to 80 parts by weight relative to 100 parts by weight of a powdery catalyst on the basis of the starting material.
6. (Original) The film-type catalyst according to claim 5, wherein the synthetic resin comprises thermosetting resin.
7. (Original) The film-type catalyst according to claim 5 or 6, wherein the synthetic resin comprises phenol resin.
8. (Currently amended) The film-type catalyst according to ~~any of claims 1 to 7~~ claim 1 or 2, wherein the substrate is a metal foil.
9. (Currently amended) The film-type catalyst according to ~~any of claims 1 to 8~~ claim 1 or 2, wherein the substrate is a honeycomb structure.

10. (Currently amended) A process for producing a tertiary amine, which comprises a step of reacting an alcohol with a primary or secondary amine in the presence of the film-type catalyst of ~~any of claims 1 to 9~~ claim 1 or 2.

11. (Canceled)